

Elastomer Type: Fluorocarbon (FKM)

Precix Compound: F139 / 75 Shore A

General Information

- True -40C FKM
- Excellent Low Temperature Resistance
- Glass Transition Temperature Tg = -43°C
- Excellent Fluid Resistance
- Excellent Heat Resistance

Applications

- Low Temperature Gaskets & Seals
- Aerospace Seals
- Refrigeration Systems
- Chemical Processing

Material

- 100% Virgin Materials
- Made in USA
- Approved to AMS7379 & is QPL Listed

Color

- Black

Operating Temperature

- -40°C to +250°C

Specific Gravity

- 1.82

Talk to an Expert! Please click here.